

Patent claims

1. Method for the manufacture of essentially endless fine threads from meltable polymers, in which polymer melt is spun from at least one spin hole and passed through a Laval nozzle, wherein the spun thread is drawn by gas streams accelerated to high speed by means of the Laval nozzle, and wherein with a given geometry of the melt hole and its position relative to the Laval nozzle the temperature of the polymer melt, its throughput per spin hole and the pressures in front of and behind the Laval nozzle which define the speed of the gas streams are controlled in such a way that the thread before solidification thereof attains a hydrostatic pressure in its interior which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.
2. Method according to claim 1, characterised in that the gas flow around the at least one thread is laminar.
3. Method according to claim 1 or claim 2, characterised in that the space behind the Laval nozzle is at ambient pressure or, in case of further processing of the threads, is at a pressure slightly above ambient pressure, which is necessary for further processing.
4. Method according to any of claims 1 to 3, characterised in that the gas streams which draw the thread are at ambient temperature or a temperature caused by their supply.
5. Method according to any of claims 1 to 4, characterised in that the ratio of the pressures in the space above and below the Laval nozzle when using air is selected between 1.02 and 2.5, depending on the polymer, its throughput and melting temperature.
6. Method according to any of claims 1 to 5, characterised in that the thread emerging from the spin hole is heated by radiation in the region of the Laval nozzle.
7. Method according to any of claims 1 to 6, characterised in that a plurality of threads are spun and split, which are deposited to form a non-woven fabric of further processed into yarns.

8. Apparatus for carrying out the method according to any of claims 1 to 7 with a spinning head connected to a feeder for the melt, a spinning nozzle assembly which is held in the spinning head and comprises at least one spin hole and which spins a melt monofilament, a plate (6') which is located below the spinning head (11) and which comprises a Laval nozzle (6) arranged in a fixed geometrical relationship to the spin hole (4), wherein between plate (6') and spinning head (11) is formed a closed first space (8) provided with a supply of gas (5) and below the plate (6') is provided a second space (7), and wherein the throughput of the melt per spin hole (4), the temperature of the melt and the pressure in the first and second spaces are adjusted in such a way that the spun melt monofilament carried by the flow of gas after leaving the Laval nozzle (6) before solidification thereof attains a hydrostatic pressure which is greater than the gas pressure surrounding it, such that the thread bursts and splits into a plurality of fine threads.
9. Apparatus according to claim 8, characterised in that the spinning assembly (3) is insulated from the first space (8) in the region of the at least one spin hole (4) by an insulating assembly (9) and/or is heated in the region of the at least one spin hole (4).
10. Apparatus according to claim 8 or 9, characterised in that the pressure ratios in the first and second spaces (8, 7) are adjusted in such a way that the gas flow in the Laval nozzle (6) attains speeds up to the speed of sound and over.
11. Apparatus according to any of claims 8 to 10, characterised in that the second space (7) is at ambient pressure or a few mbar over.
12. Apparatus according to any of claims 8 to 11, characterised in that the supplied gas is at ambient temperature or the temperature of its feeder.
13. Apparatus according to any of claims 8 to 12, characterised in that the outlet opening of the at least one spin hole (4) in the region of the Laval nozzle (6) is located at the level of the upper edge of the plate (6'), a few mm above the upper edge of the plate, or extends a few mm into the Laval nozzle (6).

- Sub
14. Apparatus according to any of claims 8 to 13, characterised in that the spinning nozzle assembly comprises a plurality of spin holes (4) which are if occasion arises provided with nipples and which form a row or several parallel rows.
15. Apparatus according to any of claims 8 to 14, characterised in that the plate comprises at least one elongate Laval nozzle.
16. Apparatus according to any of claims 8 to 14, characterised in that the plate comprises a plurality of rotationally symmetrical Laval nozzles.
17. Apparatus according to any of claims 8 to 16, characterised in that a delivery belt is provided for deposition of the threads and formation of a non-woven fabric.
18. Apparatus according to any of claims 8 to 16, characterised in that a winding device is provided for winding the threads.
19. Non-woven fabric made from threads which have been produced by the method according to any of claims 1 to 7.
20. Yarns made from threads which have been produced by the method according to any of claims 1 to 7.
- Contd.
- 19